

Wrought Stainless Steel (annealed)	(% IACS)	(Ohm-m)
201	2.50	6.90E-07
202	2.50	6.90E-07
301	2.39	7.20E-07
302	2.39	7.20E-07
302B	2.39	7.20E-07
303	2.39	7.20E-07
304	2.39	7.20E-07
302Cu	2.39	7.20E-07
304N	2.39	7.20E-07
304	2.50	6.90E-07
304	2.50	6.90E-07
305	2.39	7.20E-07
308	2.39	7.20E-07
309	2.21	7.80E-07
310	2.21	7.80E-07
314	2.24	7.70E-07
316	2.33	7.40E-07
316N	2.33	7.40E-07
316	2.30	7.50E-07
317	2.33	7.40E-07
317L	2.18	7.90E-07
321	2.39	7.20E-07
329	2.30	7.50E-07
330	1.69	1.02E-06
347	2.36	7.30E-07
347	2.40	7.18E-07
384	2.18	7.90E-07
405	2.87	6.00E-07
410	3.02	5.70E-07
414	2.46	7.00E-07
416	3.02	5.70E-07
420	3.13	5.50E-07
429	2.92	5.90E-07
430	2.87	6.00E-07
430F	2.87	6.00E-07
431	2.39	7.20E-07
434	2.87	6.00E-07
436	2.87	6.00E-07
439	2.74	6.30E-07
440A	2.87	6.00E-07
440C	2.87	6.00E-07
444	2.78	6.20E-07
446	2.57	6.70E-07
PH 13-8 Mo	1.69	1.02E-06

15-5 PH	2.24	7.70E-07
17-4 PH	2.16	8.00E-07
17-7 PH	2.08	8.30E-07
Wrought and P/M Superalloys		
Elgiloy	1.73	9.95E-07
Hastelloy "A"	1.40	1.23E-06
Hastelloy "B" & "C"	1.30	1.33E-06
Hastelloy "D"	1.50	1.15E-06
Hastelloy "X"	1.50	1.15E-06
Hastelloy "X"	1.46	1.18E-06
Haynes 150	2.13	8.10E-07
Haynes 188	1.87	9.22E-07
Haynes 230	1.38	1.25E-06
Incoloy 800	1.74	9.89E-07
Incoloy 825	1.53	1.13E-06
Incoloy 903	2.83	6.10E-07
Incoloy 907	2.47	6.97E-07
Incoloy 909	2.37	7.28E-07
Inconel 600	1.70	1.01E-06
Inconel 600	1.67	1.03E-06
Inconel 601	1.45	1.19E-06
Inconel 617	1.41	1.22E-06
Inconel 625	1.34	1.29E-06
Inconel 690	11.65	1.48E-07
Inconel 718	1.38	1.25E-06
Inconel X750	1.41	1.22E-06
L-605	1.94	8.90E-07
M-252	1.58	1.09E-06
MP35N	1.71	1.01E-06
Nimonic 263	1.50	1.15E-06
Nimonic 105	1.32	1.31E-06
Nimonic 115	1.24	1.39E-06
Nimonic 75	1.39	1.24E-06
Nimonic 80A	1.36	1.27E-06
Nimonic 90	1.46	1.18E-06
Nimonic PE.16	1.57	1.10E-06
Nimonic PK.33	1.37	1.26E-06
Rene 41	1.32	1.31E-06
Stellite 6B	1.89	9.10E-07
Udimet 500	1.43	1.20E-06
Waspaloy	1.39	1.24E-06